



TECHNICAL DATA SHEET

Product Code: D0138
Quality Standards:
ISO 9001:2015
ISO 14001: 2015
Issue Date— July2024
Revision—03

CLARETECH CSX 220 NLGI 1-2

CALCIUM SULPHONATE COMPLEX GREASE NLGI 1-2

Introduction

Claretech CSX 220 is a technologically advanced grease, formulated using over based calcium sulphonate soap thickener.

It is characterised by exceptional performance under high pressures and temperatures, with excellent resistance to water and corrosion while keeping a excellent pumpability properties.

Its inherent chemical and physical characteristics give superior anti-wear and extreme pressure properties meaning your assets are given long life protection in a wide range of industrial applications.

Applications

Claretech CSX 220 has been formulated for low temperature performance utilising a specially selected base oils. It is a multi-purpose industrial grease, used in industries such as steel and paper mills, agricultural applications and other similar conditions.

Features and Benefits

- Excellent low temperature properties
- Superior water resistance properties
- Excellent anti-oxidation and anti-corrosion properties
- Excellent pumpability
- High load rating

Typical Characteristics

| | | |
|---------------------------------------|------------|----------------------------|
| Thickener | | Calcium Sulphonate Complex |
| Appearance | Visual | Smooth Tacky |
| Colour | Visual | Beige |
| Base Oil Viscosity at 40°C | ASTM D445 | 190-210cSt |
| Worked Penetration | ASTM D217 | 290-320 |
| Drop Point | IP 396 | >250°C |
| 4 Ball Weld Load | IP 239 | 500kg |
| 4 Ball Wear Scar | IP 239 | <0.5mm |
| Water Wash Out | ASTM D1264 | <2% |
| Copper Corrosion | ASTM D4048 | 1 (no tarnish) |
| EMCOR (distilled water) | IP 220 | 0 |
| Flow Pressure at -20°C | DIN 51805 | 325 mbar |
| Flow Pressure at -35°C | DIN 51805 | <1400mbar |
| Oil Separation (40°C, 168 hrs) | IP 121 | <1% |
| Operating Temperature Range | | -30°C—160°C |

The information contained herein may change. While every care is taken to ensure the accuracy of the material contained in this bulletin, no liability can be assumed for the information given. For specific, current information please contact Clare field sales staff.